

ROPE COLOR / COLORI CORDA



- Composition: 58% Pes 42% Pan Acrylic rope, $\varnothing 6$ mm
- Breaking load: 3100 N - Elongation: 20%
- Colour fastness to artificial weathering Xenon at the fading lamp test: 7/8-8 degree, EN ISO 105-B04
- Finishing: Soil-resistant, mould resistant, oil and water-repellent with Teflon finishing.

